


HP 3D High Reusability PA 12 Glass Beads

Stiff, low-cost, quality parts



Produce stiff, functional parts

- 40% glass bead filled thermoplastic material with both optimal mechanical properties and high reusability.¹
- Provides dimensional stability along with repeatability.²
- Ideal for applications requiring high stiffness like enclosures and housings, fixtures and tooling.

Quality at a low cost per part

- Produce at a low cost per part and reduce your total cost of ownership.³
- Less waste—reuse surplus powder batch after batch and get functional parts, no throwing away anymore.¹
- Get consistent performance while achieving 70% surplus powder reusability.⁴
- Optimize cost and part quality—cost-efficient material with high surplus powder reusability.¹

Engineered for HP Multi Jet Fusion technology

- Designed for production of functional parts across a variety of industries.
- Provides the best balance between performance and reusability.⁵
- Engineered to produce common glass bead applications with detail and dimensional accuracy.

For more information, please visit
hp.com/go/3DMaterials

Technical specifications⁶

Category	Measurement	Value	Method
General properties	Powder melting point (DSC)	186 °C/367 °F	ASTM D3418
	Particle size	58 µm	ASTM D3451
	Bulk density of powder	0.48 g/cm ³	ASTM D1895
	Density of parts	1.30 g/cm ³	ASTM D792
Mechanical properties	Tensile strength, max load ⁷ , XY	30 MPa/4350 psi	ASTM D638
	Tensile strength, max load ⁷ , Z	30 MPa/4350 psi	ASTM D638
	Tensile modulus ⁷ , XY	2800 MPa/406 ksi	ASTM D638
	Tensile modulus ⁷ , Z	2900 MPa/421 ksi	ASTM D638
	Elongation at break ⁷ , XY	6.5 %	ASTM D638
	Elongation at break ⁷ , Z	6.5 %	ASTM D638
Thermal properties	Izod impact notched (@ 3.2 mm, 23°C), XYZ	2.7 KJ/m ²	ASTM D256 Test Method A
	Heat deflection temperature (@ 0.45 MPa, 66 psi), Z	173 °C/344 °F	ASTM D648 Test Method A
	Heat deflection temperature (@ 1.82 MPa, 264 psi), Z	121 °C/250 °F	ASTM D648 Test Method A
Recyclability	Refresh ratio for stable performance	30%	

Ordering Information

HP 3D High Reusability PA 12 Glass Beads		
Product Number	V1R11A	V1R22A
Weight	15 kg	150 kg
Capacity	30L ⁸	300L ⁸
Dimensions (xyz)	600 x 333 x 302 mm	800 x 600 x 1205 mm
Compatibility	HP Jet Fusion 3D 4210/4200/3200 Printing Solution	HP Jet Fusion 3D 4210/4200 Printing Solution

Eco Highlights

- Powders and agents are not classified as hazardous⁹
- Cleaner, more comfortable workplace—enclosed printing system, and automatic powder management¹⁰
- Minimizes waste due to high reusability of powder¹¹

Find out more about HP sustainable solutions at hp.com/ecosolutions

Learn more at hp.com/go/3DMaterials

1. Based on using recommended packing densities, offers high reusability of surplus powder. Liters refers to the materials container size and not the actual materials volume. Materials are measured in kilograms.
2. Testing according to ASTM D638, ASTM D256, and ASTM D648 using HDT at different loads with a 3D scanner for dimensional stability. Testing monitored using statistical process controls.
3. Compared to selective laser sintering (SLS) and fused deposition modeling (FDM) technologies, HP Multi Jet Fusion technology can reduce the overall energy requirements needed to attain full fusing and reduce the system requirements for large, vacuum-sealed ovens. In addition, HP Multi Jet Fusion technology uses less heating power than SLS systems for better material properties and material reuse rates, minimizing waste.
4. HP Jet Fusion 3D printing solutions using HP 3D High Reusability PA 12 Glass Beads provide 70% post-production surplus powder reusability, producing functional parts batch after batch. For testing, material is aged in real printing conditions and powder is tracked by generations (worst case for recyclability). Parts are then made from each generation and tested for mechanical properties and accuracy.
5. Compared to selective laser sintering (SLS) technology. Based on running a scan on the 3D printing part to measure and compare with the original STL file (using GOM software). For testing, material is aged in real printing conditions and powder is tracked by generations (worst case for recyclability). Parts are then made from each generation and tested for mechanical properties and accuracy.
6. The following technical information should be considered representative of averages or typical values and should not be used for specification purposes. These values refer to a balanced print mode with FW BD6.1.
7. Test results realized under the ASTM D638 with a test rate of 1mm/min for Z type test and a test rate of 10mm/min for XY type test, specimens type V.
8. Liters refers to the materials container size and not the actual materials volume. Materials are measured in kilograms.
9. The HP powder and agents do not meet the criteria for classification as hazardous according to Regulation (EC) 1272/2008 as amended.
10. Compared to manual print retrieval process used by other powder-based technologies. The term "cleaner" does not refer to any indoor air quality requirements and/or consider related air quality regulations or testing that may be applicable.
11. HP Jet Fusion 3D printing solutions using HP 3D High Reusability PA 12 Glass Beads material provide 70% post-production surplus powder reusability, producing functional parts batch after batch.

© Copyright 2017 HP Development Company, L.P.

Nothing herein should be construed as constituting an additional warranty. The only warranties for HP products and services are set forth in the express warranty statements accompanying such products and services and/or in a written agreement between you and HP for such HP products and services. HP believes that the information herein is correct as of the date of its publication, however, HP EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF HP IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION PROVIDED. HP shall not be liable for technical or editorial errors or omissions contained herein and the information herein is subject to change without notice. In no event shall HP be liable for damages or losses of any kind or nature that result from the use of or reliance upon this information. The HP Jet Fusion 3D Materials have not been designed, manufactured or tested by HP for compliance with legal requirements for 3D printed parts and their uses and recipients are responsible for making their own determination as to the suitability of HP Jet Fusion 3D Materials for their purposes and uses.

